



## **SPECIFICATIONS:**

# General Features

Model Name	Permeate Flow Rate GPD (L/day)	Salt Rejection %	
RE2012-100	100 (379)	98%	


- 1. The stated product performance is based on data taken after 30 minutes of operation at the following test conditions:
  - 200 mg/L NaCl solution at 60 psig (0.41 MPa) applied pressure
  - -15% recovery
  - -77 °F (25 °C)
  - -pH 6.5-7.0
- 2. Minimum salt rejection is 96.0%.
- 3. All elements are vacuum leak tested using the CSM integrity test.
- 4. Permeate flow rate for each element may vary +15/-15%.
- Elements can be supplied as dry or wet-type. Wet-tested elements are soaked in a preservative solution (1.0% food grade SBS) and vacuum sealed in a poly bag. All elements are individually boxed.

Membrane type:Thin-Film CompositeMembrane material:Polyamide (PA)

**Element configuration:** Spiral-Wound, Tape Wrapping

### **Dimensions**

Model Name	Α	В	С	D	E
RE2012-100	0.67 inch	0.47 inch	11.73 inch	0.91 inch	1.89 inch
	(17mm)	(12 mm)	(298 mm)	(23 mm)	(48 mm)



Page 1 of 2 Rev.4.0 March 2019





#### APPLICATION DATA:

#### **Operating Limits**

Max. Operating Pressure
Max. Feed Flow Rate
Max. Operating Temperature
Operating PH Range
Max. Turbidity
Max. SDI (15 min)
Max. Chlorine Concentration

The information provided in this document is solely for informative purposes. It is the user's responsibility to ensure the appropriate usage of this product. Toray Advanced Materials Korea Inc. assumes no obligation, liability or damages incurred for the misuse of the product or for the information provided in this document. This document does not express or implies any warranty as to the merchantability or fitness of the product.

#### **GENERAL HANDLING PROCEDURES**

- Elements contained in the boxes must be kept dry at room temperature (7-32°C; 40-95°F) and should not be stored in direct sunlight.
- When running the system for the first time, the permeate should be discarded continuously at least 1 hour.
- Keep elements moistly at all times after initial wetting.
- Elements should be immersed in a preservative solution during storage, shipping and system shutdowns to prevent biological growth and freezing. The standard storage solution contains 1% by weight sodium bisulfite or sodium metabisulfite (food grade). For short term storage (i.e. one week or less) 1% by weight sodium metabisulfite solution is adequate for

preventing from biological growth.

- · Keep elements moistly at all times after initial wetting.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty. For additional information on use of approved chemicals please contact your nearest CSM representative.
- Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.