

# Purolite® NRW3240

Polystyrenic Gel, Gel, Mixed Bed  
Resin, Hydrogen form, Hydroxide  
form, Nuclear Grade

## PRINCIPAL APPLICATIONS

- Primary coolant polishing

## SYSTEMS

- Clean-up systems

## TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)
- 25 L Sack - Heat sealed

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
Particle Size Range	425 - 1200 µm	
Uniformity Coefficient (max.)	1.7	
Impurities Iron (max.)	50 ppm	
Impurities Sodium (max.)	30 ppm	
Impurities Heavy Metals (max.)	40 ppm	
Anionic Form, CO <sub>3</sub> <sup>2-</sup> (max.)	5 %	
Anionic Form, SO <sub>4</sub> <sup>2-</sup> (max.)	0.1 %	
Anionic Form, Cl <sup>-</sup> (max.)	0.1 %	
Shipping Weight (approx.)	705 - 740 g/L (44.1 - 46.2 lb/ft³)	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Gel Strong Acid Cation	Gel Strong Base Anion
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H <sup>+</sup> form	OH <sup>-</sup> form
Cation / Anion Chemical Equivalent Ratio	1	1
Total Capacity (min.)	1.8 eq/L (H <sup>+</sup> form)	1 eq/L (OH <sup>-</sup> form)
Conversion (min.)	99.9 % (H <sup>+</sup> form)	95 % (OH <sup>-</sup> form)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**EMEA**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com